



PRODUCT DETAILS

Surface treatment	Oil This floor should be oiled immediately after installation.
Dimensions	1900 x 190 x 15 mm
Weight per Package (kg)	17 kg
Area per Package (m²)	2.2 m ²
Area per pallet (m²)	0 m ²
Package info	Packages may contain start and stop boards.

DETAIL DESCRIPTION

All naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

COLOUR CHANGE

Stained product - noticeable color change over time.

FACTS

Design	1-strip
Grading	Dynamic
Range	Kährs Original
Collection	Artisan Collection
Resandable	2-3 times
Natural/Stained	Stained
Joint	Woodloc® 5G
Floor heating	Yes
Warranty	30 years
Wear-layer material	Hardwood
Wear Layer Thickness (mm)	3.5 mm
Core material	Pine/Spruce lamella
Thickness (mm)	15 mm
Installation method	Glue-down, Floating
Surface Colour	White IFV

TECHNICAL PROPERTIES

Moisture content	EN13183	7%±2%
Minimum Mean Density kg/m³	>500 kg/m ³	
Reaction To Fire	EN13501-1	Dfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 x 10 ⁻⁶ n
Breaking Strength N/mm²	EN1533	NPD
Thermal Conductivity	EN12664	0,14 W/mK
Thermal Resistance R-Value	.11 (m ² K/W)	
Biological Durability	EN350-2	Class 1
CARB2	Compliant	
Slipperiness	CEN/TS15676	NPD

Other products in this collection




Maple Carob



Oak Concrete



Oak Tan



Oak Straw



Oak Oyster



Oak Linen



Oak Earth



Oak Camino

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.