



PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Surface treatment	Silk lacquer	Design	3-strip	Moisture	EN13183	7%±2%
Dimensions	2423 x 200 x 15 mm	Grading	Calm	content		
Weight per Package (kg)	23 kg	Range	Kährs Original	Minimun Mean Density kg/m³ >500 kg/m³		
Area per Package (m²)	2.9 m²	Collection	American Naturals	Reaction To Fire	EN13501-1	Dfl-s1
Area per pallet (m²) Package info	0 m ² Packages may contain	Resandable	2-3 times	Formaldehyde Emission	EN717-1	E1
r ackage into	start and stop boards.	Natural/Stained	Natural	Content PCP	CEN/TR14823	≤ 5 x 10-6n
		Brinell Value	3,6	Breaking Strength N/mm ²	EN1533	NPD
		Joint	Woodloc® 5S			
		Floor heating	Yes			
DETAIL DESCRIPTION		Warranty	30 years	Thermal Conductivity	EN12664	0,14 W/mK
Even colour with minor variations. Small sized knots in limited numbers allowed.		Wear-layer material	Hardwood	Thermal Resistance R-Value .11 (m2K/W		.11 (m2K/W)
COLOUR CHANGE		Wear Layer Thickness (mm)	3.5 mm	Biological Durability	EN350-2	Class 1
Changes from pink hues to deeper reddish brown tones.		Core material	Pine/Spruce lamella	CARB2		Compliant
		Thickness (mm)	15 mm	Slipperiness	riness CEN/TS15676 NPD	
		Installation method	Glue-down, Floating			

Other products in this collection











Walnut Georgia

Walnut Montreal

Walnut Hartford

Hard Maple Toronto



Cherry Savannah

CERTIFICATES



















Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.